

Emulsion Analysis Report
Ergon Asphalt & Emulsion Inc

14929 Slover Ave. Fontana, CA. 92337
(909)829-0505 Fax (909)829-8074

Consigned To:

Product: SS-1H

Tank No. 17

TEST RESULTS

Test on Emulsion		Test On Residue From Evaporation	
Viscosity SSF @ 77 F.	25.23	Pen @ 77 F, 100g 5sec	69.66
Residue by Distillation	60.05 %	Ductility @ 77 F 5 cm/min	150+
Oil by Distillation	trace %	Specific Gravity @ 60 F	8.5
Water Content	39.95 %	Solubility	99.7%
Settlement 5 days	0.12 %		
Storage Stability	0.24 %		
Sieve Test	0.01 %		
Cement Mix	0.02 %		

Remarks: TYPICAL LAB RESULTS

Tested By: KAJITANI

Date: 7/14/2017