



GlasPave® Paving Mat System

Specification Sheet – GlasPave50 Paving Mat

Specifications for Use in Asphalt Overlays			
Property	Test Method	GlasPave50	
		Metric*	Imperial**
Tensile Strength	ASTM D 5035	50 kN/m	280 lb/in.
Elongation at Break	ASTM D 5035	≤5%	≤5%
Melting Point	ASTM D 276	> 232°C	> 450°F
Mass/Unit Area	ASTM D 5261	237 g/m ²	7.0 oz/yd ²
Asphalt Retention	ASTM D 6140	0.47 l/m ²	0.10 gal/yd ²
Roll Sizes [†]		1.91 x 109.7 m 3.81 x 65.8 m	75 in x 120 yds 150 in x 72 yds
Roll Areas [†]		209.5 m ² 250.8 m ²	250 yd ² 300 yd ²

We believe all statements herein to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended. Values presented above are nominal and only to be used as guidelines.

[†] Product is sold by the roll. *All metric values are nominal. **All imperial values are approximate.



Tensar International Corporation
2500 Northwinds Parkway
Suite 500
Alpharetta, GA 30009
800-TENSAR-1
tensarcorp.com

GlasPave® is the registered trademark of Saint-Gobain ADFORS. GlasPave® is distributed in the United States of America, Canada and certain other countries by Tensar International Corporation (Tensar). Inasmuch as Saint-Gobain ADFORS and Tensar have no control over installation design, installation workmanship, accessory materials, or conditions of application, Saint-Gobain ADFORS and Tensar do not warrant the performance or results of any installation or use of GlasPave®. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose.

©2012, Tensar International Corporation

Exclusive distributors in the Americas for: ADFORS SAINT-GOBAIN

GP_MPDS_PAVE50_9.13